



## Standard Colors



## Premium Colors

Berridge premium colors require a nominal surcharge.



## Metallic Colors

Berridge metallic colors are premium finishes which require a nominal surcharge.



### Natural Metal Finish

Berridge Acrylic-Coated Galvalume® is a coated sheet product that combines the corrosion resistance of Galvalume® steel sheet with a clear, organic resin applied to the top side and bottom side of Galvalume® substrate.



Acrylic-Coated Galvalume®

# BERRIDGE STOCK AVAILABILITY AND COLOR DETAILS

S - Stock Color N - Non-Stocking Color N/A - Not Available

Standard Colors	24 Gauge		22 Gauge*		0.032 Aluminum*		0.040 Aluminum*		SR	EM	SRI
	48"	42"	48"	42"	48"	42"	48"	42"			
Aged Bronze	S	S	S	N	S	N	S	N/A	0.30	0.86	30
Almond	S	S	S	N	S	N	S	N/A	0.65	0.83	77
Bristol Blue	S	S	N	N	N	N	N	N/A	0.33	0.85	33
Buckskin	S	S	S	N	N	N	N	N/A	0.32	0.83	32
Burgundy	S	S	N	N	N	N	N	N/A	0.29	0.85	29
Charcoal Grey	S	S	S	N	N	N	N	N/A	0.31	0.84	30
Cityscape	S	S	N	N	N	N	N	N/A	0.48	0.85	54
Colonial Red	S	S	N	N	N	N	N	N/A	0.33	0.85	34
Copper Brown	S	S	N	N	N	N	N	N/A	0.30	0.85	29
Dark Bronze	S	S	S	N	S	N	S	N/A	0.28	0.85	27
Deep Red	S	S	N	N	N	N	N	N/A	0.39	0.84	41
Evergreen	S	S	N	N	N	N	N	N/A	0.30	0.83	29
Forest Green	S	S	S	N	N	N	N	N/A	0.25	0.83	22
Hartford Green	S	S	N	N	N	N	N	N/A	0.28	0.83	26
Hemlock Green	S	S	N	N	N	N	N	N/A	0.31	0.83	30
Matte Black	S	S	N	N	N	N	N	N/A	0.26	0.89	26
Medium Bronze	S	S	S	N	S	N	S	N/A	0.31	0.85	31
Parchment	S	S	S	N	S	N	S	N/A	0.52	0.83	58
Patina Green	S	S	N	N	N	N	N	N/A	0.34	0.86	36
Royal Blue	S	S	N	N	N	N	N	N/A	0.26	0.85	25
Shasta White	S	S	S	N	S	N	S	N/A	0.60	0.84	70
Sierra Tan	S	S	S	N	S	N	S	N/A	0.39	0.85	42
Teal Green	S	S	N	N	N	N	N	N/A	0.27	0.87	27
Terra - Cotta	S	S	N	N	N	N	N	N/A	0.32	0.83	31
Zinc Grey	S	S	S	N	S	N	S	N/A	0.39	0.85	42
Acrylic-Coated Galvalume®	S	S	S	S	N/A	N/A	N/A	N/A	0.67	0.20	59
<b>Premium Colors*</b>											
Award Blue	S	S	N	N	N	N	N	N/A	0.17	0.83	11
Natural White	S	S	N	N	N	N	N	N/A	0.76	0.84	93
<b>Metallic Colors*</b>											
Antique Copper-Cote	S	S	N	N	N	N	N	N/A	0.33	0.84	34
Champagne	S	S	N	N	N	N	N	N/A	0.40	0.85	43
Copper-Cote™	S	S	N	N	N	N	N	N/A	0.51	0.85	59
Lead-Cote™	S	S	N	N	N	N	N	N/A	0.46	0.84	50
Preweathered Galvalume®	S	S	N	N	N	N	N	N/A	0.40	0.85	43
Zinc-Cote™	S	S	N	N	N	N	N	N/A	0.53	0.83	59

## Testing results for Kynar 500®/Hylar 5000® coil coating applications:

- Specular Gloss: (ASTM D-523) Low and medium gloss only
- Color Uniformity: (ASTM D-2244) Color controlled both instrumentally and visually
- Dry Film Thickness: (ASTM D-7091, ASTM D-1005, NCCA 11-13, 11-14, 11-15) Primer 0.20 ± 0.05 mil, Topcoat 0.75 ± 0.05 mil
- Hardness: (ASTM D-3363, NCCA 11-12, Eagle Turquoise Pencils) HB Minimum
- Adhesion (X-Cut): (ASTM D-3359) No adhesion loss
- Adhesion (Crosshatch): (ASTM D-3359) No adhesion loss
- Abrasion Coefficient: (ASTM D-968) 100 liters/mil topcoat
- Direct Impact Flexibility: (ASTM D-2794, Gardner Impact Tester, 1/10" Distortion) Excellent, no removal
- Reverse Impact Flexibility: (NCCA Spec. 11, ASTM D-2794, Gardner Impact Tester, 5/8" ball Impact force in inch pounds equal to metal thickness) Excellent, no cracking or loss of adhesion
- Formability: (ASTM D-4145, 180° T-Bend on 1/8 Mandrel) No cracks or loss of adhesion
- Erosion: (20 years, 45° South Florida) Maximum 15% loss
- Humidity Resistance: (ASTM D-2247) Passes 2000 hours on Galvalume® and 4000 hours on Aluminum
- Acid Resistance: (ASTM D-1308, Proc. 3.1.1, 10% Sulfuric Acid spot test, 24 hour exposure) Excellent, no effect
- Salt Spray Resistance: (ASTM B-117) Passes 2000 hours on Galvalume® and 4000 hours on Aluminum
- Alkali Resistance: (ASTM D-1308, Proc. 5.2, 10% Sodium Hydroxide, 24 hour exposure) Excellent, no effect
- Detergent Resistance: (ASTM D-2248, 72 hours immersion in 3% solution at 100°F) Excellent, no effect
- Resistance to Acid Pollutants: (ASTM D 1308 Proc. 3.1.1, 24 hour exposure 10% HNO<sub>3</sub> vapors) Excellent, no effect
- Weathering - Color Retention: (ASTM D-2244, 20 years, 45° South Florida) Maximum 5 NBS units color change
- Weathering - Chalk Resistance: (ASTM D-4214, 20 years, 45° South Florida) Not worse than No. 8 rating

### Notes:

1. ASTM - American Society for Testing Materials
2. NCCA - National Coil Coaters Association
3. Galvalume® is 55% Aluminum-Zinc alloy coated sheet steel and is a registered trademark of BIEC International Inc.

S Stock Color; Not subject to a minimum order

N Non-Stock Color; Subject to inventory on hand; 4,500 sf minimum order for 22 Gauge and 0.032 & 0.040 Aluminum

N/A Not Available

\* Consult BMC on product availability for 22 Gauge and 0.032 and 0.040 Aluminum. Premium and Metallic colors are subject to a surcharge, contact BMC for additional information

**BMC SAN ANTONIO  
BRANCH FACILITY**  
6515 Fratt Rd.  
San Antonio, TX 78218  
210-650-3050  
Fax: 210-650-0379

**BMC HOUSTON  
BRANCH FACILITY**  
1720 Maury St.  
Houston, TX 77026  
713-223-4971  
Fax: 713-236-9422

**BMC DALLAS  
BRANCH FACILITY**  
2015 California Crossing  
Dallas, TX 75220  
972-506-8496  
Fax: 972-506-8478

**BMC DENVER  
BRANCH FACILITY**  
7505 E. 41st Ave.  
Denver, CO 80216  
303-322-3703  
Fax: 303-322-3810

**BMC CHICAGO  
BRANCH FACILITY**  
1175 Carolina Dr.  
W. Chicago, IL 60185  
630-231-7495  
Fax: 630-231-7520

**BMC RALEIGH  
BRANCH FACILITY**  
1100 Corporation Pkwy #129  
Raleigh, NC 27610  
919-537-5705  
Fax: 210-650-0379

**BMC PHOENIX  
BRANCH FACILITY**  
5717 W. Washington St.  
Phoenix, AZ 85043  
602-385-1237  
Fax: 210-650-0379

**BMC ATLANTA  
BRANCH FACILITY**  
319 Lee Industrial Blvd.  
Austell, GA 30168  
770-941-5141  
Fax: 770-941-7344

**BMC OKLAHOMA CITY  
BRANCH FACILITY**  
1400 Exchange Ave.  
Oklahoma City, OK 73108  
405-248-7404  
Fax: 210-650-0379

**BMC KANSAS CITY  
BRANCH FACILITY**  
1235 Southwest Blvd.  
Kansas City, KS 66103  
913-227-0855  
Fax: 210-650-0379

**BERRIDGE CALIFORNIA  
SALES CORPORATION\*\***  
8442 Sultana Ave.  
Fontana, CA 92335  
562-402-2081  
Fax: 562-865-7878

**BERRIDGE FLORIDA  
SALES CORPORATION\*\***  
8802 Venture Cove  
Tampa, FL 33637  
813-335-4505  
Fax: 210-650-0379

\*\*Berridge California and Florida Sales Corporations are separate entities from Berridge Manufacturing Company



**BERRIDGE MANUFACTURING COMPANY**  
Corporate & Sales Headquarters  
2610 Harry Wurzbach San Antonio, TX 78209  
210-650-3050 • Fax 210-650-0379

Manufacturing Facility  
2201 Rudeloff Rd. Seguin, TX 78155  
830-401-5200 • Fax: 830-303-0530

*Roofs of Distinction*

[www.berridge.com](http://www.berridge.com)

Spring 2018 - Berridge Color Chart - 15M Printed in the U.S.A.